

TEST REPORT

CUSTOMER: Shift 2 Ltd
Po Box 204-364
Auckland
New Zealand

CUSTOMER REFERENCE: Anna Tregoweth

TEST SPECIFICATION: Tensile testing of webbing and stitching

ITEM TESTED: Two (2) rope samples, approximately 250mm long section with a stitched in eyelet at each end.

Description	Size (mm)	Rating (kN)
Beeline	8	36


DATE OF TEST: 2 November 2012

RESULTS: The sample was subjected to a steadily increasing tensile load via 12mm diameter pins through a sewn eyelet in each end.

Sample	Ultimate tensile load (kN)	Failure Mode
1	26.58	Stitching
2	23.20	Rope at the end of Stitching

The attention of the client is drawn to the Terms and Conditions, which form part of the terms of engagement between SAI Global (NZ) Limited and the client. To access our terms and conditions please use the link:
<http://www.saiglobal.com/product-certification/downloads/ProductTestingTsandCs-lmtest.pdf>

Tested By:
James Knudsen



Checked By:
A L Carson

