

# TEST REPORT

**CUSTOMER:** Shift 2 Ltd  
Po Box 204-364  
Auckland  
New Zealand

**CUSTOMER REFERENCE:** Anna Tregoweth

**TEST SPECIFICATION:** Tensile testing of webbing and stitching

**ITEM TESTED:** Two (2) rope samples, approximately 250mm long section with a stitched in eyelet at each end.

Description	Size (mm)	Rating (kN)
Sirius	10	23

**DATE OF TEST:** 2 November 2012

**RESULTS:** The sample was subjected to a steadily increasing tensile load via 12mm diameter pins through a sewn eyelet in each end.

Sample	Ultimate tensile load (kN)	Failure Mode
1	24.99	Rope at the end of Stitching
2	23.67	Rope at the end of Stitching

The attention of the client is drawn to the Terms and Conditions, which form part of the terms of engagement between SAI Global (NZ) Limited and the client. To access our terms and conditions please use the link:  
<http://www.saiglobal.com/product-certification/downloads/ProductTestingTsandCs-Imtest.pdf>

**Tested By:**  
James Knudsen



**Checked By:**  
A L Carson

